# **Petro**Reyden

## EP-C30R

## Polypropylene Heterophasic Copolymers



#### **Product Description**

The grade is a heterophasic polypropylene copolymer for injection molding the product offers an excellent balance of stiffness.

### **Application**

- Automotive parts,
- Wells,
- Garden furniture,
- Chair shells and stadium seats.

PROPERTY	UNIT	TYPICAL VALUE	TEST METHOD
MFI	Dg/min	7.0	ISO 1133
DENSITY	g/cm3	0.9	ISO 1183
FLEXURAL MODULUS	N/mm2	1150	ISO 178
TENSILE	N/mm2	26	ISO R527
ELONGATION	%	10	ISO R527
IZOD IMPACT	Kj/m2	8	ISO 180
HARDNESS	point	68	ISO 868
VICAT	°C	151	ISO 306/A
H.D.T	°C	88	ISO 75/B

Producer: Marun Petrochemical Co.

Licensor: Basell

Packing: 25 Kg plastic bag

IMPORTANT: The information and data presented herein are based on values from respective product manufacture. Therefore, no warranty or guarantee, expressed or implied, is made nor is any accountability accepted with respect to the use of such information and data. All mentioned data are typical values and not to be considered as legally binding specification.