

EP-D 60 R

Polypropylene Heterophasic Copolymers



Product Description

EPD 60 R has a high molecular weight giving it superior toughness even at low temperature. It has excellent heat and detergent resistance,

Applications

Extrusion blow molding applications include tool boxes, auto motive parts suitcases and large containers.

PROPERTY	UNIT	TYPICAL VALUE	TEST METHOD
M.F.I	Dg/min	0.4	ISO 1133
DENSITY	g/cm ³	0.9	ISO 1183
FLEXURAL MODULUS	N/mm ²	1050	ISO 178
TENSILE	N/mm ²	26	ISO R527
ELONGATION	%	16	ISO R527
IZOD IMPACT	Kj/m ²	6.5	ISO 180
HARDNESS	point	60	ISO 868
VICAT	°C	151	ISO 306/A
H.D.T	°C	86	ISO 75/B

Producer: Marun Petrochemical Co.

Licensor: Basell

Packing: 25 Kg plastic bag

IMPORTANT: The information and data presented herein are based on values from respective product manufacture. Therefore, no warranty or guarantee, expressed or implied, is made nor is any accountability accepted with respect to the use of such information and data. All mentioned data are typical values and not to be considered as legally binding specification.