PetroReyden

LD -LH0030

Low Density Polyethylene



Product Description

LH0030 is a high molecular weight low density polyethylene film grade combining good flexible extrusion behaviour and superior mechanical properties.

Applications

General packaging applications, particularly those requiring a measure of shrink.

PROPERTIES	UNIT	TYPICAL VALUE	TEST METHOD
MFR (190°C/2.16KG)	Dg/min	0.3	ISO 1133
DENSITY	g/cm3	0.921	ISO 1183(A)
IMPACT STRENGTH	KJ/m	30	ASTM D 4272
TEAR STRENGTH(TD)	KN/m	30	ISO 6383-2
TEAR STRENGTH(MD)	KN/m	30	ISO 6383-2
YIELD STRESS (TD)	MPa	11	ISO 527
YIELD STRESS (MD)	MPa	11	ISO 527
STRAIN AT BREAK(TD)	%	500	ISO 527
STRAIN AT BREAK (MD)	%	200	ISO 527
MODULUS OF ELASTICITY (TD)	MPa	190	ISO 527
MODULUS OF ELASTICITY (MD)	MPa	190	ISO 527
COEFFICIENT OF FRICTION	-	1	ASTM D 1894
BL°CKING	g	20	Sabtec
RE-BL ^o CKING	g	10	Sabtec
HAZE	%	14	ASTM D 1003A
GLOSS	%	45	ASTM D 2457
CLARITY	mV	50	Sabtec

Film properties have been measured at 45 μm with a bur of 3.

Process conditions

LH0030 is a general purpose grade without additives. This grade offers high output and excellent drawdown.

Producer: Arya Sasol Petrochemical Co.

Licensor: Sabtec CTR®

Packing: Supplied in pellet form and can be packaged in 25kg bags, 1 ton semi bulk or 17 ton bulk.

IMPORTANT: The information and data presented herein are based on values from respective product manufacture. Therefore, no warranty or guarantee, expressed or implied, is made nor is any accountability accepted with respect to the use of such information and data. All mentioned data are typical values and not to be considered as legally binding specification.