PetroReyden

Z 30 S

Polypropylene HomoPolymer



Product Description

Moplen Z 30S is a high melt flow homopolymer for the production of low denier BCF, CF, and staple fibres at medium to high spinning speeds.

Moplen Z30S offers a high homogeneity, stable extrusion and excellent processability on both short and long spinning lines. This grade allows a high stretch ratio and gives tough and resilient fibres.

Application

- Moplen Z30S is widely used for the production of bulked continuous filament for carpet face yarns.
- Another major application is the production of high tenacity continuous filament for straps for backpacks, handles
 for big bags and safety belts. Continuous filament with medium tenacity is used for upholstery, sportswear and
 heavy duty clothing. "
- Moplen Z 30 S is all also suitable for the production of low denier staple fibres for thermos bonding

PROPERTY	UNIT	TYPICAL VALUE	TEST METHOD
MFI	Dg/min	25	ISO 1133
DENSITY	g/cm3	0.9	ISO 1183
FLEXURAL MODULUS	N/mm2	1550	ISO 178
TENSILE	N/mm2	35	ISO R527
ELONGATION AT YIELD	%	13	ISO R527
IZOD IMPACT STRENGTH	Kj/m2	3	ISO 180
HARDNESS SHORE D	point	72	ISO 868
VICAT SOFTENING POINT	°C	155	ISO 306/A
H.D.T (0.46 MPA)	°C	118	ISO 75/B

Moplen Z 30 S is suitable for food contact.

Producer: Marun petrochemical Co.

Licensor: Basell

Packing: 25 Kg plastic bag

IMPORTANT: The information and data presented herein are based on values from respective product manufacture. Therefore, no warranty or guarantee, expressed or implied, is made nor is any accountability accepted with respect to the use of such information and data. All mentioned data are typical values and not to be considered as legally binding specification.